

**Tubi secondo norme ANSI
Pipes according to standard ANSI**

Nominal Pipe Size	Outside Diameter mm	Schedule 5S		Schedule 10S		Schedule 40S		Schedule 80S		Schedule 160S		Schedule XXS	
		Thickness mm	Weight Kg/mt	Thickness mm	Weight Kg/mt	Thickness mm	Weight Kg/mt	Thickness mm	Weight Kg/mt	Thickness mm	Weight Kg/mt	Thickness mm	Weight Kg/mt
1/8"	10,3	-	-	1,24	0,28	1,73	0,37	2,41	0,47	-	-	-	-
1/4"	13,7	-	-	1,65	0,49	2,23	0,64	3,02	0,80	-	-	-	-
3/8"	17,1	-	-	1,65	0,64	2,31	0,85	3,20	1,11	-	-	-	-
1/2"	21,3	1,65	0,81	2,10	1,01	2,77	1,28	3,73	1,64	4,78	1,98	7,47	2,59
3/4"	26,7	1,65	1,03	2,10	1,29	2,87	1,71	3,91	2,22	5,56	2,93	7,82	3,69
1"	33,4	1,65	1,31	2,77	2,12	3,38	2,54	4,55	3,28	6,35	4,30	9,09	5,55
1.1/4"	42,2	1,65	1,67	2,77	2,73	3,56	3,44	4,85	4,53	6,35	5,69	9,70	8,01
1.1/2"	48,3	1,65	1,92	2,77	3,15	3,68	4,10	5,08	5,49	7,14	7,35	10,16	9,69
2"	60,3	1,65	2,42	2,77	3,99	3,91	5,52	5,54	7,60	8,74	11,29	11,07	13,65
2.1/2"	73,0	2,10	3,74	3,05	5,34	5,16	8,76	7,01	11,58	9,52	15,15	14,02	20,70
3"	88,9	2,10	4,58	3,05	6,55	5,49	11,46	7,62	15,50	11,13	21,67	15,24	28,10
3.1/2"	101,6	2,10	5,15	3,05	7,52	5,74	13,77	8,08	18,92	-	-	-	-
4"	114,3	2,10	5,81	3,05	8,49	6,02	16,32	8,56	22,66	13,49	34,05	17,12	41,66
5"	141,3	2,77	9,46	3,40	11,74	6,55	22,10	9,52	31,44	15,88	49,87	19,05	58,21
6"	168,3	2,77	11,3	3,40	14,03	7,11	28,69	10,97	43,21	18,26	68,59	21,95	80,53
8"	219,1	2,77	14,8	3,76	20,0	8,18	43,20	12,70	65,63	23,01	112,6	22,22	109,4
10"	273,0	3,40	22,6	4,19	27,8	9,27	61,21	12,70	83,15	28,58	175,8	-	-
12"	232,9	3,96	31,2	4,57	36,2	9,52	75,28	12,70	99,37	33,32	243,2	-	-

